


# PL-RuO<sub>4</sub> MP-Resin      PL-IO<sub>4</sub> MP-Resin



## Description


Polymer supported perruthenate

## Synonyms

Quaternary amine resin, perruthenate form; PSP

## Applications

These polymer supported oxidizing agents are attached to a specially prepared ion exchange resin, optimized for small molecule synthesis applications. Polymer supported periodate is also capable of cleaving 1,2-diols.




## Description

Polymer supported periodate

## Synonyms

Quaternary amine resin, periodate form



## References

- Harrison, C R & Hodge, P (1982) , J Chem Soc, Perkin Trans 1, 509  
 Villemin, D & Richard, M (1982), Nouv J Chim, **6**, 605  
 Hinzen, B & Ley, S V (1997), J Chem Soc, Perkin Trans 1, 1907  
 Hinzen, B & Ley, S V (1998), J Chem Soc, Perkin Trans 1, 1  
 Hinzen, B et al (1998), J Chem Soc, Perkin Trans 1, 2235  
 Ley, S V et al (1998), J Chem Soc, Perkin Trans 1, 2239  
 Bolli, M H & Ley, S V (1998), J Chem Soc, Perkin Trans 1, 2243  
 Hinzen, B et al (1998), Synthesis, 977  
 Ley, S V et al (1999), J Chem Soc, Perkin Trans 1, 1251  
 Habermann, J et al (1999), J Chem Soc, Perkin Trans 1, 1253  
 Drewry, D H et al (1999), Med Res Rev, **19**, 97

## Products Information

Macroporous

### PL-RuO<sub>4</sub> MP-Resin

0.4mmol/g 100Å 150-300µm (50-100 mesh)

### PL-IO<sub>4</sub> MP-Resin

1.4mmol/g 100Å 150-300µm (50-100 mesh)